

Classification of reaction to fire in accordance with EN 13501-1

1 Introduction

This classification report defines the classification assigned to “Wooden cladding for outdoor rainscreen, with edge type Dobbelfals TETT” in accordance with the procedure given in EN 13501-1:2018.

2 Details of classified product

2.1 General

According to the client:

Product called “Wooden cladding for outdoor rainscreen” with edge type Dobbelfals TETT”. The product has nominal properties according to the table below.

Product	Specie	Nominal thickness and width (mm)	Product nominal density (kg/m ³)	Vacuum-pressure impregnation process. Type and uptake kg/m ³ (dry).
Wooden cladding for outdoor rainscreen	Spruce	19 x 148	450	Wolmanit KD 10 uptake 5.0 kg/m ³

The impregnation is applied to the panel in a vacuum-pressure impregnation process.

According to the owner of this classification report, this product complies with the European product specification EN 14915:2013+A2:2020.

2.2 Product description

The product, is fully described above or is fully described in the test reports provided in support of classification listed in Clause 3.1.

RISE Research Institutes of Sweden AB

Postal address
Box 857
501 15 BORÅS
SWEDEN

Office location
Brinellgatan 4
504 62 Borås
SWEDEN

Phone / Fax / E-mail
+46 10-516 50 00
+46 33-13 55 02
info@ri.se

This report may not be reproduced other than in full, except with the prior written approval of the issuing laboratory.



3 Reports and results in support of this classification

3.1 Test reports

Table 1 Test reports forming the basis for this classification.

Name of laboratory	Name of sponsor	Test report reference no	Accredited test methods and date
RISE	Bergene Holm AS	O100352-136614-1	EN 13823:2020 and EN ISO 11925-2:2020

3.2 Test results

Table 2 Test results showing the worst case as found in the test program performed.

Test method	Parameter	Number of tests	Results	
			Continuous parameter mean (m)	Compliance with parameters
EN ISO 11925-2		12		
Edge/Surface flame attack**				
30 s exposure	$F_s \leq 150$ mm		(-)	Compliant
Flaming droplets/particles	Ignition of filter paper		(-)	No ignition of filter paper
EN 13823		3		
	$FIGRA_{0,2MJ}$ (W/s)		644	Compliant
	$FIGRA_{0,4MJ}$ (W/s)		644	Compliant
	$LFS < \text{edge}$		(-)	Compliant
	THR_{600s} , (MJ)		15	Compliant
	$SMOGRA$, (m ² /s ²)		13	Compliant
	TSP_{600s} , (m ²)		22	Compliant
	Flaming droplets/particles		(-)	No flaming droplets/particles

** : as required to the end use application of the product

(-) : not applicable

4 Classification and field of application

4.1 Reference of classification

This classification has been carried out in accordance with clause 11 and 15 of EN 13501-1:2018.

4.2 Classification

The product called “Wooden cladding for outdoor rainscreen” with edge type “Dobbelfals TETT” in relation to its reaction to fire behaviour is classified:

D

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming particles/droplets is:

d0

The format of the reaction to fire classification for construction products excluding floorings and linear pipe thermal insulation product is:

Fire Behaviour		Smoke Production				Flaming Droplets	
D	-	s	1	,	d	0	

Reaction to fire classification: *D-s1,d0*

4.3 Field of application:

This classification is valid for the following product parameters:

Product description, as specified in 2.1 in this report

Nominal thickness: 19 mm.

Nominal density: 450 kg/m³

Impregnation type and dry uptake: Wolmanit KD 10, 5.0 kg/m³.

This classification is valid for the following end use conditions:

Substrates

- Gypsum plasterboard (paper faced) and any end use substrate of Euroclasses A1 or A2-s1,d0 at least 12 mm thick, having a density $\geq 525 \text{ kg/m}^3$.

Fixings

- Mechanically fixed.

Joints

- Horizontal and vertical joints.

Void

- Mounted with or without a void.

The sample was delivered by the client. RISE, Fire Technology was not involved in the sampling procedure.

5 Limitations

This classification document does not represent type approval or certification of the product.

RISE Research Institutes of Sweden AB
Department Fire Technology - Reaction to Fire Medium Scale Lab

Performed by

Examined by

Richard Johansson

Per Thureson